

## Eurotec® Tecodur® PB70 GR50 BK009 MX01 PBT/PET, 50% glass fiber reinforced, heat & UV stabilized, improved impact, natural

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET Blend, Glass Filled , Polybutylene Terephthalate (PBT), Heat Resistant , Polybutylene Terephthalate (PBT), Impact Grade , Polyethylene Terephthalate (PET)

### Material Notes:

Information provided by Eurotec®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eurotec-Tecodur-PB70-GR50-BK009-MX01-PBTPET-50-glass-fiber-reinforced-heat-UV-stabilized-improved-impact-natural.php](http://www.lookpolymers.com/polymer_Eurotec-Tecodur-PB70-GR50-BK009-MX01-PBTPET-50-glass-fiber-reinforced-heat-UV-stabilized-improved-impact-natural.php)

Physical Properties	Metric	English	Comments
Density	1.73 g/cc	0.0625 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.100 % @Temperature 23.0 °C	0.100 % @Temperature 73.4 °F	50% RH; ISO 960

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ISO 527
Elongation at Break	2.0 %	2.0 %	ISO 527
Tensile Modulus	17.0 GPa	2470 ksi	ISO 527
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180/1A
	11.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	5.23 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180/1A

Thermal Properties	Metric	English	Comments
Melting Point	225 - 255 °C	437 - 491 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	
	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	260 - 280 °C	500 - 536 °F	
Feed Temperature	50.0 - 70.0 °C	122 - 158 °F	Throat
Mold Temperature	60.0 - 110 °C	140 - 230 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 960
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China