

Eurotec® Tecolen® CP10 GR10 NL PPCP, 10% glass fiber reinforced, natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Glass Fiber Filler

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecolen-CP10-GR10-NL-PPCP-10-glass-fiber-reinforced-natural.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	ISO 527
Elongation at Break	7.0 %	7.0 %	ISO 527
Tensile Modulus	2.50 GPa	363 ksi	ISO 527
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	20.0 kJ/m ²	9.52 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	160 - 165 °C	320 - 329 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	200 - 240 °C	392 - 464 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	20.0 - 50.0 °C	68.0 - 122 °F	
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China