

Eurotec® Tecolen® HP30 NL XC30 PPHP, flame retardant - halogen (RoHS compliant), heat stabilized, natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecolen-HP30-NL-XC30-PPHP-flame-retardant-halogen-RoHS-compliant-heat-stabilized-natural.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	ISO 527
Elongation at Break	>= 100 %	>= 100 %	ISO 527
Tensile Modulus	1.25 GPa	181 ksi	ISO 527
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	8.00 kJ/m ²	3.81 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	165 - 170 °C	329 - 338 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75
Flammability, UL94	V-2	V-2	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	775 °C	1430 °F	GWIT; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	950 °C	1740 °F	GWF1; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	200 - 240 °C	392 - 464 °F	
Feed Temperature	<= 60.0 °C	<= 140 °F	Throat
Mold Temperature	20.0 - 50.0 °C	68.0 - 122 °F	
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China