

ExxonMobil Escorene® LD-705 High EVA Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A fractional melt index, 13.3% vinyl acetate copolymer specialty film resin for applications requiring outstanding heat sealability, strength, and toughness. Applications: Primal meat wrap; Pallet stretch wrap; Heat seal layer in blown film coextrusions and laminations; Liquid packaging; Profile extrusions; Compounding; Frozen food bags.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-705-High-EVA-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in ³	Exxon Method
Environmental Stress Crack Resistance	>= 500 hour	>= 500 hour	F50, Condition A; ASTM D1693
Melt Flow	0.40 g/10 min	0.40 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84	84	ASTM D2240
Hardness, Shore D	33	33	ASTM D2240
Tensile Strength, Ultimate	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.0830 GPa	12.0 ksi	1% Secant, ASTM D790
Tensile Impact Strength	732 kJ/m ²	348 ft-lb/in ²	23°C; ASTM D-1822

Thermal Properties	Metric	English	Comments
Melting Point	92.0 °C	198 °F	Exxon Method
Vicat Softening Point	77.0 °C	171 °F	1000g; ASTM D-1525

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China