

ExxonMobil Escorene® LD-760 High EVA Compounding Resin (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 27.5% vinyl acetate copolymer designed for specialty compounding applications.

Excellent filler acceptance produces highly loaded concentrates. Applications: Compounding; Concentrates; Electrical applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-760-High-EVA-Compounding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	Exxon Method
Environmental Stress Crack Resistance	>= 500 hour	>= 500 hour	F50, Condition A; ASTM D1693
Melt Flow	2.3 g/10 min	2.3 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	ASTM D2240
Hardness, Shore D	26	26	ASTM D2240
Tensile Strength, Ultimate	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.0260 GPa	3.77 ksi	1% Secant, ASTM D790
Tensile Impact Strength	805 kJ/m ²	383 ft-lb/in ²	23°C; ASTM D-1822

Thermal Properties	Metric	English	Comments
Melting Point	73.0 °C	163 °F	Exxon Method
Vicat Softening Point	51.0 °C	124 °F	1000g; ASTM D-1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China