

## ExxonMobil Escorene® LD-783 EVA Copolymer for Specialty Applications (discontinued \*\*)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

### Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 33% vinyl acetate copolymer. Applications: Soft, injection molded parts; Low modulus applications.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Escorene-LD-783-EVA-Copolymer-for-Specialty-Applications-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LD-783-EVA-Copolymer-for-Specialty-Applications-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.956 g/cc	0.0345 lb/in <sup>3</sup>	Exxon Method
Apparent Bulk Density	0.577 g/cc	0.0208 lb/in <sup>3</sup>	ASTM D1895 (B)
Melt Flow	43 g/10 min	43 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	3.00 MPa	435 psi	ASTM D638
Elongation at Break	1050 %	1050 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	61.0 °C	142 °F	Exxon Method
Vicat Softening Point	105 °C	221 °F	Softening Point, R&B; ASTM E-28

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China