

ExxonMobil Escorene™ UL 00226CC Ethylene Vinyl Acetate Copolymer (European Grade)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

Product Description: UL 00226CC is a copolymer of ethylene and vinyl acetate. **Processing Conditions:** Processing temperature above 230°C (446°F) may cause resin degradation. **Availability:** Africa & Middle East and Europe **Additive:** Antiblock: NoSlip: No Thermal Stabilizer: Yes **Applications:** Compounding Hot Melt Adhesives Injection Molding Profile Extrusion Tube Extrusion Wire and Cable Compounds Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-UL-00226CC-Ethylene-Vinyl-Acetate-Copolymer-European-Grade.php

Physical Properties	Metric	English	Comments
Density	0.951 g/cc	0.0344 lb/in ³	ExxonMobil method
Vinyl Acetate Content	26 %	26 %	ExxonMobil method
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 0.689 MPa	>= 100 psi	Molded Properties; ISO 527-2/1A/100
Tensile Modulus	0.0193 GPa	2.80 ksi	Molded Properties; ISO 527-2/1

Thermal Properties	Metric	English	Comments
Melting Point	<= 163 °C	<= 325 °F	Peak Melting Point; ExxonMobil method
Vicat Softening Point	46.7 °C	116 °F	ASTM D1525

Descriptive Properties	Value	Comments
Blending Temperature	230	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China