

## ExxonMobil Escorene® UL-7760 EVA Copolymer, Adhesive and Sealant Grade (discontinued \*\*)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

### Material Notes:

Data provided by the manufacturer, Exxon Chemical. A 28% vinyl acetate copolymer. Applications: Hot melt adhesives; Wax blends; Industrial sealants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-Escorene-UL-7760-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued.php](http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-UL-7760-EVA-Copolymer-Adhesive-and-Sealant-Grade-nbspdiscontinued.php)

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in <sup>3</sup>	Exxon Method
Viscosity	5700 cP @Temperature 121 °C	5700 cP @Temperature 250 °F	melt viscosity; ASTM D-3236
Melt Flow	5.7 g/10 min	5.7 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	12.0 MPa	1740 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	72.0 °C	162 °F	Exxon Method
Vicat Softening Point	150 °C	302 °F	Softening Point, R&B; ASTM E-28

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China