

ExxonMobil Geolast® 701-70 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A soft, black, oil resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good hot air and hot oil resistance for use in a wide range of applications. This grade of Geolast TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable. Recyclable. Designed for improved fluid resistance. Information provided by Advanced Elastomer Systems

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Geolast-701-70-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 g/cc	1.00 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	.12 in; ASTM D2240
	71	71	Air at 257°F, 168 hr; ASTM D573
Tensile Strength at Break	4.45 MPa	645 psi	257°F, 70 hr in IRM 903 Oil; ASTM D471
	5.93 MPa	860 psi	Across Flow; ASTM D412
	6.700 MPa	971.8 psi	Air at 257°F, 168 hr; ASTM D573
Tensile Strength, Ultimate	3.31 MPa	480 psi	Across Flow; ASTM D412
Elongation at Break	189.8 %	189.8 %	257°F, 70 hr in IRM 903 Oil; ASTM D471
	249.6 %	249.6 %	Air at 257°F, 168 hr; ASTM D573
	260 %	260 %	Across Flow; ASTM D412
Tear Strength	18.9 kN/m	108 pli	73°C, Die C; ASTM D624
Compression Set	25 %	25 %	158°F, 22 hr; ASTM D395
	33 %	33 %	257°F, 70 hr; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-37.2 °C	-35.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	

Processing Properties	Metric °C	English °F	Comments
Descriptive Properties			
		Value	Comments
Change in Mass in IRM 903 Oil at 257°F for 70 hr		0.72	
Color		Black	
Form		Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China