

## ExxonMobil LDPE LD 105.30 Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

### Material Notes:

**Product Description:** LD 105 resins are homopolymer packaging film resins designed for applications requiring outstanding clarity with good stiffness. These resins can be processed in either blown or cast film equipment. In blown film equipment LD 105.30 can be drawn down to 1.0 mil gauge.  
**Availability:** Latin America, North America and South America  
**Additive:** Antiblock: 1000 ppm  
**Slip:** No  
**Thermal Stabilizer:** Yes  
**Applications:** Blend Partner Bread Bags Display Packaging Film Food packaging Form Fill and Seal Packaging Freezer Film High Clarity Film High Quality Lamination Lamination Film Laundry Film Light Duty Shrink Film Produce Bags Salad Bags Textile Packaging  
 Information provided by ExxonMobil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-LDPE-LD-10530-Low-Density-Polyethylene-Resin.php](http://www.lookpolymers.com/polymer_ExxonMobil-LDPE-LD-10530-Low-Density-Polyethylene-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in <sup>3</sup>	ExxonMobil method
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Antiblock Level	1000 ppm	1000 ppm	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ASTM D882
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ASTM D882
Film Elongation at Break, MD	210 %	210 %	ASTM D882
Film Elongation at Break, TD	570 %	570 %	ASTM D882
Puncture Energy	0.757 J	0.558 ft-lb	ExxonMobil Method
Elmendorf Tear Strength MD	350 g	350 g	ASTM D1922
Elmendorf Tear Strength TD	180 g	180 g	ASTM D1922
Dart Drop Test	100 g	0.221 lb	ASTM D1709A
Film Tensile Strength at Break, MD	24.8 MPa	3600 psi	ASTM D882
Film Tensile Strength at Break, TD	21.4 MPa	3100 psi	ASTM D882
1% Secant Modulus, MD	214 MPa	31000 psi	ASTM D882
1% Secant Modulus, TD	255 MPa	37000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	<= 232 °C	<= 450 °F	Peak Melting Point; ExxonMobil method

Optical Properties	Metric	English	Comments
Haze	5.2 %	5.2 %	ASTM D1003
Gloss	76 %	76 %	45°; ASTM D2457

Descriptive Properties	Value	Comments
Puncture Force	8 lbf	ExxonMobil Method

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China