

ExxonMobil LLDPE LL 1002.80 Linear Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product Description: LL 1002 resins are butane LLDPE designed for the blown film process. Films made from LL 1002 resins have very good tensile and toughness properties. LL 1002.09 is a granular material which, while it can be used for film production, is also suitable for compounding.
Availability: Latin America, North America and South America
Additive: Antiblock: 3500 ppm
Slip: 1500 ppm
Processing Aid: No
Thermal Stabilizer: Yes
Applications: Agricultural Film, Bag in Box, Blown Film, Cast Film, Food packaging, Form Fill and Seal, Packaging, Freezer Film, Garment Film, General Packaging, Industrial Packaging, Liners, Mulch Film, Packaging Films, Produce Bags on a Roll, Shoppers, Trash Can Liners.
 Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LLDPE-LL-100280-Linear-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ExxonMobil method
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Antiblock Level	3500 ppm	3500 ppm	
Slip Level	1500 ppm	1500 ppm	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	8.27 MPa	1200 psi	ASTM D882
Film Tensile Strength at Yield, TD	8.27 MPa	1200 psi	ASTM D882
Film Elongation at Break, MD	660 %	660 %	ASTM D882
Film Elongation at Break, TD	780 %	780 %	ASTM D882
Puncture Energy	1.10 J	0.808 ft-lb	ExxonMobil Method
Elmendorf Tear Strength MD	120 g	120 g	ASTM D1922
Elmendorf Tear Strength TD	340 g	340 g	ASTM D1922
Dart Drop Test	70.0 g	0.154 lb	ASTM D1709A
Film Tensile Strength at Break, MD	36.5 MPa	5300 psi	ASTM D882
Film Tensile Strength at Break, TD	26.2 MPa	3800 psi	ASTM D882
1% Secant Modulus, MD	179 MPa	26000 psi	ASTM D882
1% Secant Modulus, TD			ASTM D882

Mechanical Properties	193 MPa Metric	28000 psi English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	<= 253 °C	<= 487 °F	Peak Melting Point; ExxonMobil method
Optical Properties	Metric	English	Comments
Haze	29 %	29 %	ASTM D1003
Gloss	22 %	22 %	45°; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China