

## ExxonMobil PP7011L1 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

### Material Notes:

**Product Description:** An impact copolymer resin for extrusion applications with high melt viscosity and excellent low-temperature impact strength. It is suitable for cables, pipes, profiles, sheets and thermoforming. **Availability:** Africa & Middle East and Europe **Features:** High Impact Resistance Low Flow Uses: Compounding Corrugated Pipe Electrical/Electronic Applications Industrial Applications **Processing Method:** Extrusion, Extrusion Blow Molding, Injection Molding, Profile Extrusion, Sheet Extrusion and Thermoforming **Automotive Specifications:** Daimler Chrysler DBL 5404 Information provided by ExxonMobil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ExxonMobil-PP7011L1-Polypropylene-Impact-Copolymer.php](http://www.lookpolymers.com/polymer_ExxonMobil-PP7011L1-Polypropylene-Impact-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ExxonMobil Method
Melt Flow	1.0 g/10 min	1.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	
	4.0 g/10 min	4.0 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 230 °C	@Load 11.0 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ISO 868
Tensile Strength, Yield	26.0 MPa	3770 psi	ISO 527-2/50
Elongation at Yield	10 %	10 %	ISO 527-2/50
Tensile Modulus	1.10 GPa	160 ksi	Secant; ISO527-2/1
Flexural Modulus	1.15 GPa	167 ksi	Secant; ISO 178
Izod Impact, Notched (ISO)	35.7 kJ/m <sup>2</sup>	17.0 ft-lb/in <sup>2</sup>	ISO 180/1A
Charpy Impact, Notched	0.441 J/cm <sup>2</sup>	2.10 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.609 J/cm <sup>2</sup>	2.90 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	3.36 J/cm <sup>2</sup>	16.0 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	322 °C	612 °F	ISO 3146
Crystallization Temperature	234 °C	453 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	82.8 °C	181 °F	ISO 75-2/B
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ISO 75-2/A
Vicat Softening Point	149 °C	300 °F	ISO 306/A50

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China