

ExxonMobil Santoprene® 201-55W175 Thermoplastic Elastomer (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A soft, colorable thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance, and is designed for thin wall or complex profile extrusion applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for extrusion. It is polyolefin based and completely recyclable. Designed for thin wall extrusion applications. Recommended for applications requiring excellent flex fatigue resistance. Recommended for applications requiring excellent ozone resistance. Information provided by Advanced Elastomer Systems

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-201-55W175-Thermoplastic-Elastomer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	.12 in; ASTM D2240
Tensile Strength at Break	4.41 MPa	640 psi	Across Flow; ASTM D412
Tensile Strength, Ultimate	2.00 MPa	290 psi	Across Flow; ASTM D412
Elongation at Break	370 %	370 %	Across Flow; ASTM D412

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	

Descriptive Properties	Value	Comments
Change in Mass in IRM 903 Oil at 257°F for 70 hr	35	
Color	Natural Color	
Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China