

ExxonMobil Santoprene® 8211-75 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A soft, colorable, non-hygroscopic thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in difficult injection molding applications. This grade of Santoprene 8000 TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and completely recyclable. Key Features: Non-hygroscopic product, requires little to no drying before processing. Neutral, easy coloring formulation. Recommended for applications requiring excellent ozone resistance. Used in sealing applications. Recommended for applications requiring excellent flex fatigue resistance. UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Although not NSF certified, this product has a Material Supplier Form on file with NSF to facilitate its evaluation for use in applications requiring NSF certification. EU and China RoHS compliant. Applications: Automotive – Interior Consumer – Electronics, Floor Care, Hand Tools and Kitchen Tools Soft Touch Grips Uses: Automotive Applications Cell Phones Consumer Applications Flexible Grips Seals Processing Method: Blow Molding, Extrusion Blow Molding, Injection Blow Molding, Injection Molding and Multi Injection Molding Availability: Africa & Middle East, Europe, North America, Asia Pacific, Latin America and South America Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-8211-75-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	2 mm, 15 sec; ISO 868
Tensile Strength at Break	5.837 MPa	846.6 psi	Air at 302°F, 168 hr; ASTM D573
	7.03 MPa	1020 psi	Across Flow; ASTM D412
Tensile Stress	3.80 MPa	551 psi	Across Flow; ASTM D412
	@Strain 100 %	@Strain 100 %	
Elongation at Break	317.2 %	317.2 %	Air at 302°F, 168 hr; ASTM D573
	520 %	520 %	Across Flow; ASTM D412
Compression Set	36 %	36 %	158°F, 22 hr; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746
UL RTI, Electrical	100 °C	212 °F	UL 746

Thermal Properties with Impact	90.0 °C Metric	194 °F English	Comments
	@Thickness 1.10 mm	@Thickness 0.0433 in	
	95.0 °C	203 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	HB	HB	
	@Thickness 1.10 mm	@Thickness 0.0433 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	
Rear Barrel Temperature	177 - 191 °C	351 - 376 °F	
Middle Barrel Temperature	179 - 193 °C	354 - 379 °F	
Front Barrel Temperature	185 - 199 °C	365 - 390 °F	
Nozzle Temperature	185 - 210 °C	365 - 410 °F	
Melt Temperature	143 - 216 °C	289 - 421 °F	Processing
Mold Temperature	10.0 - 51.7 °C	50.0 - 125 °F	Processing
Moisture Content	0.080 %	0.080 %	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Clamp Pressure	41.4 - 68.9 MPa	6000 - 10000 psi	
Vent Depth	0.00254 cm	0.00100 in	
Cushion	0.317 - 0.635 cm	0.125 - 0.250 in	
Screw Speed	100 - 200 rpm	100 - 200 rpm	

Descriptive Properties	Value	Comments
Color	Natural Color	
Form	Pellets	
Injection Rate	Fast	
Maximum Regrind %	20	
Screw Compression Ratio	2:1 - 2.5:1	

Descriptive Properties

Value 20:1

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China