

ExxonMobil VISTANEX™ L-140

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-VISTANEX-L-140.php

| Physical Properties | Metric | English | Comments |
|---|-------------------------|-------------------------|-------------------|
| Specific Gravity | 0.920 g/cc | 0.920 g/cc | |
| Molecular Weight | 1.88e+6 - 2.34e+6 g/mol | 1.88e+6 - 2.34e+6 g/mol | Viscosity average |
| Ash | <= 0.30 % | <= 0.30 % | |
| Collected Volatile Condensable Material | <= 0.30 % | <= 0.30 % | |

| Descriptive Properties | Value | Comments |
|------------------------|-------------|----------|
| Anti oxidant | 0.05 ± 0.04 | wt % |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China