

## Fainplast Compounds EVAtech 801S Ethylene Vinyl Acetate Foam

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

### Material Notes:

EVA (ethylene-vinyl acetate) designed for the production of crosslinked expanded products using injection technology. Information provided by Fainplast Compounds

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-EVAtech-801S-Ethylene-Vinyl-Acetate-Foam.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-EVAtech-801S-Ethylene-Vinyl-Acetate-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.320 - 0.380 g/cc	0.0116 - 0.0137 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore C	59 - 65	59 - 65	ASTM D2240
Tensile Strength at Break	>= 3.20 MPa	>= 464 psi	ISO 527
Elongation at Break	>= 380 %	>= 380 %	ISO 527

Thermal Properties	Metric	English	Comments
CTE, linear	140 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	77.8 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
Shrinkage	<= 1.8 % @Temperature 70.0 $^\circ\text{C}$ , Time 86400 sec	<= 1.8 % @Temperature 158 $^\circ\text{F}$ , Time 24.0 hour	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 190 $^\circ\text{C}$	356 - 374 $^\circ\text{F}$	
Shelf Life	3.00 Month	3.00 Month	Moisture absorption after extended storage

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China