

## Fainplast Compounds HL 84 Flexible PVC, Insulation for High Temperatures

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

General purposes

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-HL-84-Flexible-PVC-Insulation-for-High-Temperatures.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-HL-84-Flexible-PVC-Insulation-for-High-Temperatures.php)

Physical Properties	Metric	English	Comments
Density	1.41 - 1.45 g/cc	0.0509 - 0.0524 lb/in <sup>3</sup>	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82 - 86	82 - 86	ISO R 868
Tensile Strength at Break	>= 15.0 MPa	>= 2180 psi	ISO R 527
Elongation at Break	>= 300 %	>= 300 %	ISO R 527

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+14 ohm-cm @Temperature 23.0 °C	2.00e+14 ohm-cm @Temperature 73.4 °F	ASTM D257

Descriptive Properties	Value	Comments
Thermal Stability (minutes)	150	CEI 20-34/3-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China