

## Fainplast Compounds Hax™ HFX 515 Crosslinkable HFFR Cable Compound

Category : Polymer , Thermoplastic , Polyolefin , Polyolefin , Wire/Cable Grade

**Material Notes:**

Polyolefin based HFFR silane grafted compound; cross-linkable by heat and moisture and by addition of suitable catalyst  
 description:• Sheathing, Insulation  
 Information provided by Fainplast Compounds

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-Hax-HFX-515-Crosslinkable-HFFR-Cable-Compound.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-Hax-HFX-515-Crosslinkable-HFFR-Cable-Compound.php)

Physical Properties	Metric	English	Comments
Density	1.39 - 1.43 g/cc	0.0502 - 0.0517 lb/in <sup>3</sup>	ISO 1183
Melt Flow	4.5 g/10 min @Load 21.6 kg, Temperature 150 °C	4.5 g/10 min @Load 47.6 lb, Temperature 302 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	42 - 48	42 - 48	ISO 868
Tensile Strength	13.0 MPa	1890 psi	Crosslinked specimen; ISO 527
Elongation at Break	250 %	250 %	Crosslinked specimen; ISO 527

Thermal Properties	Metric	English	Comments
Oxygen Index	33 %	33 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+16 ohm-cm	>= 1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	120 - 200 °C	248 - 392 °F	
Shelf Life	3.00 Month @Temperature 30.0 °C	3.00 Month @Temperature 86.0 °F	Moisture absorption after extended storage

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China