

## Fainplast Compounds KL 93 Flexible PVC, Insulation for High Temperatures Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

**Material Notes:**

Operatine temperature 105°C

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fainplast-Compounds-KL-93-Flexible-PVC-Insulation-for-High-Temperatures-Lead-Free.php](http://www.lookpolymers.com/polymer_Fainplast-Compounds-KL-93-Flexible-PVC-Insulation-for-High-Temperatures-Lead-Free.php)

Physical Properties	Metric	English	Comments
Density	1.37 - 1.41 g/cc	0.0495 - 0.0509 lb/in <sup>3</sup>	ISO R 1184

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90 - 94	90 - 94	ISO R 868
Tensile Strength at Break	>= 15.0 MPa	>= 2180 psi	ISO R 527
Elongation at Break	>= 260 %	>= 260 %	ISO R 527

Descriptive Properties	Value	Comments
Thermal Stability (minutes)	300	CEI 20-34/3-2

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China