

Fainplast Compounds RE 236 Rigid PVC, Extrusion

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Electric channels

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-RE-236-Rigid-PVC-Extrusion.php

Physical Properties	Metric	English	Comments
Density	1.60 - 1.64 g/cc	0.0578 - 0.0592 lb/in ³	ISO R 1184

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	ISO R 527
Tensile Strength, Yield	36.0 MPa	5220 psi	ISO R527
Elongation at Break	100 %	100 %	ISO R 527
Izod Impact, Unnotched	0.400 - 0.800 J/cm @Temperature 23.0 °C	0.749 - 1.50 ft-lb/in @Temperature 73.4 °F	ISO R180

Thermal Properties	Metric	English	Comments
Vicat Softening Point	80.0 - 82.0 °C @Load 5.00 kg	176 - 180 °F @Load 11.0 lb	ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China