

## Ferro IP 730 Passivation Glasses (Pb-B-Si-Al; Pb-Si-Al; Si-Pb-Al Silicates)

Category : Ceramic , Glass , Oxide , Silicon Oxide

### Material Notes:

Glass Type: Pb-B-Si-Al Typical Powder Form: TF, REG, RWG, SRRG Ferro's passivation glasses are designed for use on transistors, thyristors, and diodes. These products are formulated and produced to achieve very low alkali and iron levels and can be applied by a variety of techniques including photo-spin, spin coat, doctor blading, sedimentation, screen printing, and electrophoresis. Information provided by Ferro Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ferro-IP-730-Passivation-Glasses-Pb-B-Si-Al-Pb-Si-Al-Si-Pb-Al-Silicates.php](http://www.lookpolymers.com/polymer_Ferro-IP-730-Passivation-Glasses-Pb-B-Si-Al-Pb-Si-Al-Si-Pb-Al-Silicates.php)

Physical Properties	Metric	English	Comments
Density	3.89 g/cc	0.141 lb/in <sup>3</sup>	
Particle Size	1.5 Åµm	1.5 Åµm	50% of particles, (SRRG Powder)
	3.0 Åµm	3.0 Åµm	50% of particles, (RWG Powder)
	7.0 Åµm	7.0 Åµm	50% of particles, (REG Powder)
	9.0 Åµm	9.0 Åµm	50% of particles, (TF Powder)
	<= 10 Åµm	<= 10 Åµm	SRRG Powder
	<= 25 Åµm	<= 25 Åµm	RWG Powder
	<= 75 Åµm	<= 75 Åµm	REG Powder
	<= 75 Åµm	<= 75 Åµm	TF Powder

Thermal Properties	Metric	English	Comments
CTE, linear	5.50 Åµm/m-Å°C	3.06 Åµin/in-Å°F	
	@Temperature 25.0 - 260 Å°C	@Temperature 77.0 - 500 Å°F	
Softening Point	610 Å°C	1130 Å°F	
Transformation Temperature	465 Å°C	869 Å°F	

Chemical Properties	Metric	English	Comments
Ionic Impurities - Na (Sodium)	<= 30 ppm	<= 30 ppm	TF, REG Powders
	<= 50 ppm	<= 50 ppm	RWG, SRRG Powders
Ionic Impurities - K (Potassium)	<= 10 ppm	<= 10 ppm	TF, REG Powders
	<= 30 ppm	<= 30 ppm	RWG, SRRG Powders

Chemical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	<= 200 Â°C	<= 392 Â°F	Maximum Junction Temperature
	660 Â°C	1220 Â°F	Typical Firing Temperature; Typical Firing Time: 10-15 min. at Peak

Descriptive Properties	Value	Comments
Ionic Impurities - Li (Lithium) ppm, Max	10	RWG, SRRG Powders
	10	TF, REG Powders

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China