

Formosa Plastics Formolene® 3335E Random Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Random Copolymer for Clear Storage Boxes, Pill Vials and Containers Formolene® 3335E is a high melt flow random copolymer with fast cycle time and easy mold release. It is designed for injection molding including thin wall applications. The use of an advanced clarifier produces a material with low yellowness index and haze – which makes it an excellent choice for 'see-through' house wares and rigid packaging. Formolene® 3335E meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. Specimens were injection molded according to the conditions specified in ASTM D4101 Information provided by Formosa Plastics Corporation, USA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-3335E-Random-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D1505
Melt Flow	35 g/10 min @Temperature 230 °C	35 g/10 min @Temperature 446 °F	I ₂ ; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.0 MPa	4200 psi	2" (50mm) per min; ASTM D638
Elongation at Yield	15 %	15 %	2" (50mm) per min; ASTM D638
Flexural Modulus	1.03 GPa	150 ksi	1.3mm per min, 1% secant; ASTM D790
Izod Impact, Notched	0.641 J/cm @Temperature 23.0 °C	1.20 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	85.0 °C	185 °F	ASTM D648

Optical Properties	Metric	English	Comments
Haze	12 % @Thickness 1.00 mm	12 % @Thickness 0.0394 in	Injection Haze Plaque; FTTC 5606

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China