

Formosa Plastics Formolene® HB5502B2 Blow Molding HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

Hexene Copolymer Applications: Pharmaceutical Packaging; Personal Care Products; Bleach and Detergents Industrial; and Chemicals & Parts
Formolene® HB5502B2 is designed for applications requiring excellent stiffness and stress crack resistance properties. It may be used as a general-purpose blow molding resin or sheet extrusion thermoforming resin. Formolene® HB5502B2 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact. Information provided by Formosa Plastics Corporation, USA.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-HB5502B2-Blow-Molding-HDPE.php

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	35 hour	35 hour	Condition B, F ₅₀ ; ASTM D1693
	45 hour	45 hour	Condition A (100% Igepal), F ₅₀ ; ASTM D1693
Melt Flow	0.35 g/10 min @Load 2.16 kg, Temperature 190 °C	0.35 g/10 min @Load 4.76 lb, Temperature 374 °F	Condition E; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	2" (50mm) per min.; ASTM D638 Type IV
Elongation at Break	>= 600 %	>= 600 %	2" (50mm) per min.; ASTM D638 Type IV
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -118 °C	<= -180 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China