

## Formosa Plastics Formolene® L42022E2 Film (Butene Grade) LLDPE

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

### Material Notes:

Butene Copolymer (Low slip and antiblock) Applications: Thin gauge blown film Thin gauge blown film Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact. Film properties taken from sample 25 Microns thick, at a 4:1 Blow Up Ratio, 160 X 2.5 mm die, 250 lbs./hr Information provided by Formosa Plastics Corporation, USA.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Formosa-Plastics-Formolene-L42022E2-Film-Butene-Grade-LLDPE.php](http://www.lookpolymers.com/polymer_Formosa-Plastics-Formolene-L42022E2-Film-Butene-Grade-LLDPE.php)

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D1505
Thickness	25.0 microns	0.984 mil	
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	Condition E; ASTM D1238
Antiblock Level	7000 ppm	7000 ppm	
Slip Level	1350 ppm	1350 ppm	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Film Elongation at Break, TD	800 %	800 %	ASTM D882
Elmendorf Tear Strength, MD	4.33 g/micron	110 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	22.4 g/micron	570 g/mil	ASTM D1922
Dart Drop	2.56 g/micron	65.0 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	26.9 MPa	3900 psi	ASTM D882
Film Tensile Strength at Break, TD	18.6 MPa	2700 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	35 %	35 %	ASTM D1003
Gloss	40 %	40 %	45°; ASTM D2457

Descriptive Properties	Value	Comments
------------------------	-------	----------

Blow Up Ratio  
Descriptive Properties

4 to 1  
Value

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China