

Freudenberg Simrit V178 Non-Black Compound

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Specific compounding ingredients can reduce or eliminate the presence of carbon black. These compounds may provide improved resistance to oxidative environments and reactive plasmas. The inorganic pigments are not recommended for use in wet chemical environments as they have been shown to increase the extractable ionic contamination.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Freudenberg-Simrit-V178-Non-Black-Compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	
Tensile Strength, Ultimate	15.7 MPa	2280 psi	
Elongation at Break	160 %	160 %	
Compression Set	16 %	16 %	
	@Temperature 200 Â°C, Time 252000 sec	@Temperature 392 Â°F, Time 70.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 Â°C	392 Â°F	
Minimum Service Temperature, Air	-20.0 Â°C	-4.00 Â°F	

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China