

Garlock 9520 Fluoroelastomer Sheet Rubber Gasketing

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer

Material Notes:

Fluoroelastomer (FKM) Type A Exceptional resistance to heat, oils, fuels, numerous acids, and many other chemicals. Information provided by Garlock Rubber Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Garlock-9520-Fluoroelastomer-Sheet-Rubber-Gasketing.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70 - 80	70 - 80	ASTM D 2240
Tensile Strength	6.89 MPa	1000 psi	ASTM F152
Elongation at Break	>= 180 %	>= 180 %	ASTM D 395
Compression Set	<= 50 % @Temperature 175 Â°C, Time 79200 sec	<= 50 % @Temperature 347 Â°F, Time 22.0 hour	ASTM D 395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	204 Â°C @Pressure 1.72 MPa	400 Â°F @Pressure 250 psi	
Minimum Service Temperature, Air	-26.1 Â°C	-15.0 Â°F	

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China