

## Gichem GILAC C120/T Acrylonitrile Butadiene Styrene (discontinued \*\*)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

### Material Notes:

ABS with excellent thermal properties. Medium-High Injection speed. Information provided by GICHEM Gruppo Industriale Chimico

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gichem-GILAC-C120T-Acrylonitrile-Butadiene-Styrene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Gichem-GILAC-C120T-Acrylonitrile-Butadiene-Styrene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	ASTM D638
Elongation at Yield	20 %	20 %	ASTM D638
Flexural Modulus	2.50 GPa	363 ksi	ASTM D790
Izod Impact, Notched	1.20 J/cm	2.25 ft-lb/in	ASTM D256
	0.700 J/cm	1.31 ft-lb/in	ASTM D256
	@Temperature 0.000 °C	@Temperature 32.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	106 °C	223 °F	ASTM D648
Vicat Softening Point	108 °C	226 °F	ASTM D1525/A
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Flammability Test	75	75	[°C] Bilia; IEC 331
Oxygen Index	19 %	19 %	ASTM D2863
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	220 °C	428 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	30.0 - 60.0 °C	122 - 140 °F	
Drying Temperature	80.0 °C	176 °F	2 hours

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China