

## Glastic Laminates/Shapes UTS Fiberglass-Reinforced Polyester Laminate

Category : Polymer , Thermoset , Composite SMC , Filled/Reinforced Thermoset , Polyester, TS , Thermoset Polyester Glass Filled BMC

**Material Notes:**

Data provided by Glastic Corporation.NEMA GPO-2.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Glastic-LaminatesShapes-UTS-Fiberglass-Reinforced-Polyester-Laminate.php](http://www.lookpolymers.com/polymer_Glastic-LaminatesShapes-UTS-Fiberglass-Reinforced-Polyester-Laminate.php)

Mechanical Properties	Metric	English	Comments
Flexural Strength	170 MPa	24700 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	155 Â°C	311 Â°F	NEMA temperature
UL RTI, Electrical	130 Â°C	266 Â°F	
UL RTI, Mechanical with Impact	160 Â°C	320 Â°F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Arc Resistance	130 sec	130 sec	ASTM D495

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China