

Goodfellow Iron 60/Titanium 40 Alloy

Category : Metal , Ferrous Metal , Superalloy , Iron Base

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-Iron-60Titanium-40-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	1380 °C	2520 °F	

Component Elements Properties	Metric	English	Comments
Iron, Fe	60 %	60 %	
Titanium, Ti	40 %	40 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China