

Gouda Vuurvast CURAS 50 D Moldable Refractory Material

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Description: Because of special additions this moldable already has a reasonable strength at room temperature. This material is supplied as a dry powder, it has to be mixed with potable water to the necessary consistency. (Depends on the type of work)Remarks: The stated chemical composition and physical properties represent average values.Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-CURAS-50-D-Moldable-Refractory-Material.php

Physical Properties	Metric	English	Comments
Bulk Density	2.20 - 2.30 g/cc	0.0795 - 0.0831 lb/in ³	After drying at 110 ^o C

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.700 - 0.800 W/m-K	4.86 - 5.55 BTU-in/hr-ft ² - ^o F	
	@Temperature 100 ^o C	@Temperature 212 ^o F	
	0.830 - 0.930 W/m-K	5.76 - 6.45 BTU-in/hr-ft ² - ^o F	
	@Temperature 600 ^o C	@Temperature 1110 ^o F	
	0.960 - 1.06 W/m-K	6.66 - 7.36 BTU-in/hr-ft ² - ^o F	
	@Temperature 1400 ^o C	@Temperature 2550 ^o F	
Maximum Service Temperature, Air	1500 ^o C	2730 ^o F	
Shrinkage	-2.00 - 2.00 %	-2.00 - 2.00 %	Permanent Linear Change
	@Temperature 1400 ^o C	@Temperature 2550 ^o F	

Component Elements Properties	Metric	English	Comments
Al2O3	50 %	50 %	
Fe2O3	2.0 %	2.0 %	
SiO2	40 %	40 %	

Descriptive Properties	Value	Comments
Bonding Type	chemical/ceramic	
Material Consumption per 1 m3	2200 kg	

Descriptive Properties	Value	Comments
Mixing Water	9-11 liters	per 100 kgs dry material
Segercone	33	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China