

GrafTech eGRAF[®] HITHERM[™],ç HT-720 Graphite

Category : Carbon , Graphite

Material Notes:

Made from natural graphite, eGRAF[®] HITHERM[™],ç thermal interface materials are designed for use in applications requiring low contact resistance and high thermal conductivity. HITHERM[™],ç material is offered in a variety of through thickness thermal conductivities, available in roll or die-cut form and can be laminated with plastics and adhesives. An economical thermal interface material, HITHERM[™],ç products will not dry out and no outgassing occurs under vacuum conditions. The conformability of HITHERM[™],ç materials optimizes thermal properties, ensures excellent contact, and is maintained for the life of the assembly. Typical applications include thermal interfaces, chip burn-in, chip testing fixtures, DC-to-DC converters, CPU modules, microprocessors, and hot and cold plates.

Order this product through the following link:

http://www.lookpolymers.com/polymer_GrafTech-eGRAF-HITHERM-HT-720-Graphite.php

Physical Properties	Metric	English	Comments
Thickness	508 microns	20.0 mil	

Thermal Properties	Metric	English	Comments
CTE, linear	-0.400 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	-0.222 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	In-Plane
	27.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	15.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Through Thickness
Specific Heat Capacity	0.711 J/g- $\text{Å}^\circ\text{C}$	0.170 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	6.00 W/m-K	41.6 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	Through Thickness; ASTM-D5470 Modified (at 110kPa/16 psi/1.1 bar)
	240 W/m-K	1670 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	In-Plane; Angstrom's Method
Maximum Service Temperature, Air	400 $\text{Å}^\circ\text{C}$	752 $\text{Å}^\circ\text{F}$	
Minimum Service Temperature, Air	-40.0 $\text{Å}^\circ\text{C}$	-40.0 $\text{Å}^\circ\text{F}$	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00100 ohm-cm	0.00100 ohm-cm	In-Plane
	1.50 ohm-cm	1.50 ohm-cm	Through Thickness

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China