

## Gromax BFG30-FU00B3 Nylon 6 30% Glass Filled (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gromax-BFG30-FU00B3-Nylon-6-30-Glass-Filled-Dry.php](http://www.lookpolymers.com/polymer_Gromax-BFG30-FU00B3-Nylon-6-30-Glass-Filled-Dry.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ISO 1183
Moisture Absorption	0.900 %	0.900 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.0028 cm/cm @Temperature 80.0 Â°C	0.0028 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0069 cm/cm @Temperature 80.0 Â°C	0.0069 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4
Melt Flow	32 g/10 min @Load 5.00 kg, Temperature 275 Â°C	32 g/10 min @Load 11.0 lb, Temperature 527 Â°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	91	91	[N/mm<sup>2<sup></sup>]; ISO 7619
Tensile Strength	174.8 MPa	25350 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	2.6 %	2.6 %	50 mm/min; ISO 527
Tensile Modulus	9.55 GPa	1390 ksi	1 mm/min; ISO 527-1,-2
Flexural Strength	262.7 MPa	38100 psi	5 mm/min; ISO 178
Flexural Modulus	8.52 GPa	1240 ksi	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	10.7 kJ/mÂ²	5.09 ft-lb/inÂ²	ISO 180-1A
Charpy Impact Unnotched	7.70 J/cmÂ² @Temperature 23.0 Â°C	36.6 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179-1eU
Charpy Impact, Notched	1.14 J/cmÂ² @Temperature 23.0	5.42 ft-lb/inÂ²	ISO 179-1A

Mechanical Properties	°C Metric	@Temperature 73.4 °F English	Comments
<b>Thermal Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Melting Point	220 °C	428 °F	10°C/min; ISO 11357-1,-3
Deflection Temperature at 0.46 MPa (66 psi)	215.1 °C	419.2 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	205.2 °C	401.4 °F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 °C	518 - 554 °F	ISO 294
Mold Temperature	80.0 - 120 °C	176 - 248 °F	ISO 294
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China