

Gromax CFG35-R113N1 Nylon 6 36% Glass Filled (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 40% Glass Fiber Filled

Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-CFG35-R113N1-Nylon-6-36-Glass-Filled-Dry.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Moisture Absorption	0.860 %	0.860 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Temperature 80.0 Â°C	0.0030 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0070 cm/cm @Temperature 80.0 Â°C	0.0070 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	88	88	[N/mm²]; ISO 7619
Tensile Strength	182 MPa	26500 psi	50 mm/min; ISO 527
Elongation at Break	3.3 %	3.3 %	50 mm/min; ISO 527
Flexural Strength	260 MPa	37700 psi	5 mm/min; ISO 178
Flexural Modulus	8.83 GPa	1280 ksi	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	17.0 kJ/mÂ²	8.09 ft-lb/inÂ²	ISO 180-1A
Charpy Impact Unnotched	9.00 J/cmÂ² @Temperature 23.0 Â°C	42.8 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179-1eU
Charpy Impact, Notched	1.77 J/cmÂ² @Temperature 23.0 Â°C	8.42 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179-1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	226 Â°C	439 Â°F	ISO 75-1,-2

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.60 mm	@Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	266 - 280 Â°C	511 - 536 Â°F	ISO 294
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	ISO 294
Drying Temperature	80.0 Â°C	176 Â°F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China