

## Haynes Hastelloy® B-3 alloy, 6.3 mm plate

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

### Material Notes:

The attributes of Corrosion-Resistant HASTELLOY® alloys include high resistance to uniform attack, outstanding localized corrosion resistance, excellent stress corrosion cracking resistance, and ease of welding and fabrication. Same excellent resistance to hydrochloric acid and other strongly reducing chemicals as B-2 alloy, but with significantly better thermal stability, fabricability and stress corrosion cracking resistance. In The As-Welded Condition HASTELLOY® B-3 alloy is an additional member of the nickel-molybdenum family of alloys with excellent resistance to hydrochloric acid at all concentrations and temperatures. It also withstands sulfuric, acetic, formic and phosphoric acids, and other nonoxidizing media. B-3 alloy has excellent resistance to pitting corrosion, to stress-corrosion cracking and to knife-line and heat-affected zone attack. The improved thermal stability of HASTELLOY B-3 alloy minimizes the problems associated with fabrication of B-2 alloy components. This is due to the reduced tendency to precipitate deleterious intermetallic phases in B-3 alloy, thereby, affording it greater ductility than B-2 alloy during and following various thermal cycling conditions. HASTELLOY B-3 alloy has good overall forming and welding characteristics. It may be forged or otherwise hotworked, providing that it is held at 2250°F (1230°C) for a time sufficient to bring the entire piece to temperature. Since it is a low carbon alloy, the use of lower hot finishing temperatures may be necessary to achieve grain size control. B-3 alloy may also be formed by cold working. Although it does work-harden somewhat rapidly, B-3 alloy components can be made using all common cold forming techniques. Limited tests in boiling 20 percent hydrochloric acid indicate that the uniform corrosion resistance of B-3 alloy is not affected by cold reductions up to 50 percent as compared to that of the alloy in the solution heat-treated condition. B-3 alloy can be welded by all common welding techniques, although oxyacetylene and submerged arc welding processes are not recommended when the fabricated item is to be used in corrosive service. Special precautions should be taken to avoid excessive heat input. Heat Treatment: All wrought forms of HASTELLOY B-3 alloy are furnished in the solution heat treated condition unless otherwise specified. B-3 alloy is solution heat-treated at 1950°F (1065°C) and rapid quenched, except for bright annealed sheet or coil products which are heat-treated at 2100°F (1150°C) and cooled in hydrogen. Applications: HASTELLOY B-3 alloy is suitable for use in all applications previously requiring the use of HASTELLOY B-2 alloy. Like B-2 alloy, B-3 is not recommended for use in the presence of ferric or cupric salts as these salts may cause rapid corrosion failure. Ferric or cupric salts may develop when hydrochloric acid comes in contact with iron or copper. ASME Boiler And Pressure Vessel Code ASME has published Code Case 2140 for solution annealed HASTELLOY B-3 alloy

Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Haynes-Hastelloy-B-3-alloy-63-mm-plate.php](http://www.lookpolymers.com/polymer_Haynes-Hastelloy-B-3-alloy-63-mm-plate.php)

Physical Properties	Metric	English	Comments
Density	9.22 g/cc	0.333 lb/in <sup>3</sup>	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	885 MPa	128000 psi	
	730 MPa	106000 psi	
	@Temperature 540 °C	@Temperature 1000 °F	
	735 MPa	107000 psi	

Mechanical Properties	Metric	English	Comments
	@Temperature 650 Â°C	@Temperature 1200 Â°F	
	745 MPa	108000 psi	
	@Temperature 425 Â°C	@Temperature 797 Â°F	
	765 MPa	111000 psi	
	@Temperature 315 Â°C	@Temperature 599 Â°F	
	795 MPa	115000 psi	
	@Temperature 205 Â°C	@Temperature 401 Â°F	
	845 MPa	123000 psi	
	@Temperature 95.0 Â°C	@Temperature 203 Â°F	
<b>Tensile Strength, Yield</b>	400 MPa	58000 psi	
	@Strain 0.200 %	@Strain 0.200 %	
	275 MPa	39900 psi	
	@Strain 0.200 %, Temperature 540 Â°C	@Strain 0.200 %, Temperature 1000 Â°F	
	285 MPa	41300 psi	
	@Strain 0.200 %, Temperature 425 Â°C	@Strain 0.200 %, Temperature 797 Â°F	
	290 MPa	42100 psi	
	@Strain 0.200 %, Temperature 650 Â°C	@Strain 0.200 %, Temperature 1200 Â°F	
	305 MPa	44200 psi	
	@Strain 0.200 %, Temperature 315 Â°C	@Strain 0.200 %, Temperature 599 Â°F	
	330 MPa	47900 psi	
	@Strain 0.200 %, Temperature 205 Â°C	@Strain 0.200 %, Temperature 401 Â°F	
	375 MPa	54400 psi	
	@Strain 0.200 %, Temperature 95.0 Â°C	@Strain 0.200 %, Temperature 203 Â°F	
<b>Elongation at Break</b>	57.8 %	57.8 %	in 51 mm
	58.2 %	58.2 %	in 51 mm
	@Temperature 95.0 Â°C	@Temperature 203 Â°F	

Mechanical Properties	60.9 % Metric	60.9 % English	in 51 mm Comments
	@Temperature 205 Å°C 61.6 %	@Temperature 401 Å°F 61.6 %	in 51 mm
	@Temperature 315 Å°C	@Temperature 599 Å°F	
	61.7 %	61.7 %	in 51 mm
	@Temperature 425 Å°C	@Temperature 797 Å°F	
	61.7 %	61.7 %	in 51 mm
	@Temperature 540 Å°C	@Temperature 1000 Å°F	
	64.6 %	64.6 %	in 51 mm
	@Temperature 650 Å°C	@Temperature 1200 Å°F	
Reduction of Area	67.5 %	67.5 %	
	54.9 %	54.9 %	
	@Temperature 650 Å°C	@Temperature 1200 Å°F	
	61.5 %	61.5 %	
	@Temperature 540 Å°C	@Temperature 1000 Å°F	
	64.9 %	64.9 %	
	@Temperature 425 Å°C	@Temperature 797 Å°F	
	65.5 %	65.5 %	
	@Temperature 315 Å°C	@Temperature 599 Å°F	
	67.3 %	67.3 %	
	@Temperature 95.0 Å°C	@Temperature 203 Å°F	
	68.1 %	68.1 %	
	@Temperature 205 Å°C	@Temperature 401 Å°F	
Modulus of Elasticity	216 GPa	31300 ksi	RT
	147 GPa	21300 ksi	
	@Temperature 1000 Å°C	@Temperature 1830 Å°F	
	157 GPa	22800 ksi	
	@Temperature 900 Å°C	@Temperature 1650 Å°F	

Mechanical Properties	Metric	English	Comments
	@Temperature 800 Â°C	@Temperature 1470 Â°F	
	178 GPa	25800 ksi	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	185 GPa	26800 ksi	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	190 GPa	27600 ksi	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	197 GPa	28600 ksi	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	202 GPa	29300 ksi	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	208 GPa	30200 ksi	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	213 GPa	30900 ksi	
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	11.4 Âµm/m-Â°C	6.33 Âµin/in-Â°F	
	@Temperature 25.0 - 300 Â°C	@Temperature 77.0 - 572 Â°F	
	11.6 Âµm/m-Â°C	6.44 Âµin/in-Â°F	
	@Temperature 25.0 - 400 Â°C	@Temperature 77.0 - 752 Â°F	
	11.8 Âµm/m-Â°C	6.56 Âµin/in-Â°F	
	@Temperature 25.0 - 600 Â°C	@Temperature 77.0 - 1110 Â°F	
	11.8 Âµm/m-Â°C	6.56 Âµin/in-Â°F	
@Temperature 25.0 - 500 Â°C	@Temperature 77.0 - 932 Â°F		
12.2 Âµm/m-Â°C	6.78 Âµin/in-Â°F		
@Temperature 25.0 - 700 Â°C	@Temperature 77.0 - 1290 Â°F		

Thermal Properties	Metric	English	Comments
	@Temperature 25.0 - 800 Å°C	@Temperature 77.0 - 1470 Å°F	
	13.9 Åµm/m-Å°C	7.72 Åµin/in-Å°F	
	@Temperature 25.0 - 900 Å°C	@Temperature 77.0 - 1650 Å°F	
	14.4 Åµm/m-Å°C	8.00 Åµin/in-Å°F	
	@Temperature 25.0 - 1000 Å°C	@Temperature 77.0 - 1830 Å°F	
Specific Heat Capacity	0.373 J/g-Å°C	0.0891 BTU/lb-Å°F	RT
	0.382 J/g-Å°C	0.0913 BTU/lb-Å°F	
	@Temperature 100 Å°C	@Temperature 212 Å°F	
	0.409 J/g-Å°C	0.0978 BTU/lb-Å°F	
	@Temperature 200 Å°C	@Temperature 392 Å°F	
	0.421 J/g-Å°C	0.101 BTU/lb-Å°F	
	@Temperature 300 Å°C	@Temperature 572 Å°F	
	0.431 J/g-Å°C	0.103 BTU/lb-Å°F	
	@Temperature 400 Å°C	@Temperature 752 Å°F	
	0.434 J/g-Å°C	0.104 BTU/lb-Å°F	
	@Temperature 600 Å°C	@Temperature 1110 Å°F	
	0.436 J/g-Å°C	0.104 BTU/lb-Å°F	
	@Temperature 500 Å°C	@Temperature 932 Å°F	
	0.575 J/g-Å°C	0.137 BTU/lb-Å°F	
	@Temperature 1000 Å°C	@Temperature 1830 Å°F	
	0.577 J/g-Å°C	0.138 BTU/lb-Å°F	
	@Temperature 900 Å°C	@Temperature 1650 Å°F	
	0.589 J/g-Å°C	0.141 BTU/lb-Å°F	
	@Temperature 800 Å°C	@Temperature 1470 Å°F	
	0.595 J/g-Å°C	0.142 BTU/lb-Å°F	
	@Temperature 700 Å°C	@Temperature 1290 Å°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000137 ohm-cm	0.000137 ohm-cm	RT
	0.000130 ohm-cm @Temperature 1000 Â°C	0.000130 ohm-cm @Temperature 1830 Â°F	
	0.000132 ohm-cm @Temperature 900 Â°C	0.000132 ohm-cm @Temperature 1650 Â°F	
	0.000137 ohm-cm @Temperature 800 Â°C	0.000137 ohm-cm @Temperature 1470 Â°F	
	0.000137 ohm-cm @Temperature 100 Â°C	0.000137 ohm-cm @Temperature 212 Â°F	
	0.000137 ohm-cm @Temperature 200 Â°C	0.000137 ohm-cm @Temperature 392 Â°F	
	0.000138 ohm-cm @Temperature 300 Â°C	0.000138 ohm-cm @Temperature 572 Â°F	
	0.000138 ohm-cm @Temperature 400 Â°C	0.000138 ohm-cm @Temperature 752 Â°F	
	0.000140 ohm-cm @Temperature 500 Â°C	0.000140 ohm-cm @Temperature 932 Â°F	
	0.000142 ohm-cm @Temperature 700 Â°C	0.000142 ohm-cm @Temperature 1290 Â°F	
	0.000143 ohm-cm @Temperature 600 Â°C	0.000143 ohm-cm @Temperature 1110 Â°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China