

Haynes Multimet® alloy, GTAW, 6.35 mm plate

Category : Metal , Superalloy , Iron Base

Material Notes:

Recommended for use in applications involving high stress at temperatures up to 816Â°C (1500Â°F), and moderate stresses up to 1093Â°C (2000Â°F). Excellent oxidation resistance, good ductility, and is readily fabricated. Current applications include aircraft, including tailpipes and tailcones, afterburner parts, exhaust manifolds, combustion chambers, turbine blades, buckets and nozzles. Excellent service for high temperature bolts. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Multimet-alloy-GTAW-635-mm-plate.php

Physical Properties	Metric	English	Comments
Density	8.20 g/cc	0.296 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	768 MPa	111000 psi	
Elongation at Break	21 %	21 %	in 50.8 mm
Poissons Ratio	0.298	0.298	RT
	0.315	0.315	
	@Temperature 426 Â°C	@Temperature 799 Â°F	
	0.319	0.319	
	@Temperature -78.0 Â°C	@Temperature -108 Â°F	
	0.325	0.325	
	@Temperature 650 Â°C	@Temperature 1200 Â°F	
	0.339	0.339	
	@Temperature 816 Â°C	@Temperature 1500 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	15.3 Âµm/m-Â°C	8.50 Âµin/in-Â°F	
	@Temperature 23.0 - 300 Â°C	@Temperature 73.4 - 572 Â°F	
	15.6 Âµm/m-Â°C	8.67 Âµin/in-Â°F	
	@Temperature 23.0 - 400 Â°C	@Temperature 73.4 - 752 Â°F	

Thermal Properties	Metric	English	Comments
	@Temperature 23.0 - 500 Å°C	@Temperature 73.4 - 932 Å°F	
	16.7 Åµm/m-Å°C	9.28 Åµin/in-Å°F	
	@Temperature 23.0 - 600 Å°C	@Temperature 73.4 - 1110 Å°F	
	17.2 Åµm/m-Å°C	9.56 Åµin/in-Å°F	
	@Temperature 23.0 - 700 Å°C	@Temperature 73.4 - 1290 Å°F	
	17.5 Åµm/m-Å°C	9.72 Åµin/in-Å°F	
	@Temperature 23.0 - 800 Å°C	@Temperature 73.4 - 1470 Å°F	
	17.8 Åµm/m-Å°C	9.89 Åµin/in-Å°F	
	@Temperature 23.0 - 1000 Å°C	@Temperature 73.4 - 1830 Å°F	
	17.8 Åµm/m-Å°C	9.89 Åµin/in-Å°F	
	@Temperature 23.0 - 900 Å°C	@Temperature 73.4 - 1650 Å°F	
	18.4 Åµm/m-Å°C	10.2 Åµin/in-Å°F	
	@Temperature 23.0 - 1100 Å°C	@Temperature 73.4 - 2010 Å°F	
Specific Heat Capacity	0.435 J/g-Å°C	0.104 BTU/lb-Å°F	
	@Temperature >=100 Å°C	@Temperature >=212 Å°F	
Thermal Conductivity	15.9 W/m-K	110 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 300 Å°C	@Temperature 572 Å°F	
	17.3 W/m-K	120 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 400 Å°C	@Temperature 752 Å°F	
	18.6 W/m-K	129 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 500 Å°C	@Temperature 932 Å°F	
	20.0 W/m-K	139 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 600 Å°C	@Temperature 1110 Å°F	
	20.0 W/m-K	139 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 200 Å°C	@Temperature 392 Å°F	
Melting Point	1288 - 1354 Å°C	2350 - 2469 Å°F	

Thermal Properties	Metric ^{°C}	English ^{°F}	Comments
Liquidus	1354 \hat{A} °C	2469 \hat{A} °F	

Optical Properties	Metric	English	Comments
Emissivity (0-1)	0.88 @Temperature 1090 \hat{A} °C	0.88 @Temperature 1990 \hat{A} °F	Oxidized

Component Elements Properties	Metric	English	Comments
Carbon, C	0.080 - 0.16 %	0.080 - 0.16 %	
Cb + Ta	0.75 - 1.25 %	0.75 - 1.25 %	
Chromium, Cr	20 - 22.5 %	20 - 22.5 %	
Cobalt, Co	18.5 - 21 %	18.5 - 21 %	
Iron, Fe	33 %	33 %	As remainder
Manganese, Mn	1.0 - 2.0 %	1.0 - 2.0 %	
Molybdenum, Mo	2.5 - 3.5 %	2.5 - 3.5 %	
Nickel, Ni	19 - 21 %	19 - 21 %	
Nitrogen, N	0.10 - 0.20 %	0.10 - 0.20 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Tungsten, W	2.0 - 3.0 %	2.0 - 3.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000930 ohm-cm @Temperature 22.0 \hat{A} °C	0.0000930 ohm-cm @Temperature 71.6 \hat{A} °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China