

Heatbath/Park #800 High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Working range covers temperatures frequently used in hardening and tempering steel. This product is also used as a high speed quench and draw. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-800-High-Speed-Hardening-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	454 Â°C	850 Â°F	
Maximum Service Temperature, Air	677 Â°C	1250 Â°F	Upper limit of working range
Minimum Service Temperature, Air	496 Â°C	925 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China