

Heatbath/Park AL-2 High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

A mixture of nitrates in granular form especially formulated as an economical bath for tempering tool steels requiring treatment within its working range. This highly fluid bath offers low dragout because of its fast drainage properties. Applicable when chloride salts are not wanted. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-AL-2-High-Speed-Hardening-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	260 Â°C	500 Â°F	
Maximum Service Temperature, Air	593 Â°C	1100 Â°F	Upper limit of working range
Minimum Service Temperature, Air	288 Â°C	550 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China