

Heatbath/Park AL-2 for Aluminum Solution Heat Treating

Category : Ceramic , Fluid , Quenchant

Material Notes:

A granular mixture of sodium and potassium nitrates formulated per MIL-H-6088. It is less costly than Tempering C-ALHT with only a slight sacrifice in working range. It is colored pink for identification purposes. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-AL-2-for-Aluminum-Solution-Heat-Treating.php

Thermal Properties	Metric	English	Comments
Melting Point	260 Â°C	500 Â°F	
Maximum Service Temperature, Air	593 Â°C	1100 Â°F	Upper limit of working range
Minimum Service Temperature, Air	288 Â°C	550 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China