

## Heatbath/Park High Speed 60 High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

**Material Notes:**

Solution Treating Salt. A neutral salt designed for heat treatment high alloy steels requiring temperatures of 1650Â° to 2200Â°F.

Formulated per MIL-S-10699-B, Class 6. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HeatbathPark-High-Speed-60-High-Speed-Hardening-Salt.php](http://www.lookpolymers.com/polymer_HeatbathPark-High-Speed-60-High-Speed-Hardening-Salt.php)

| Thermal Properties               | Metric   | English  | Comments                     |
|----------------------------------|----------|----------|------------------------------|
| Melting Point                    | 871 Â°C  | 1600 Â°F |                              |
| Maximum Service Temperature, Air | 1260 Â°C | 2300 Â°F | Upper limit of working range |
| Minimum Service Temperature, Air | 927 Â°C  | 1700 Â°F | Lower limit of working range |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China