

## Heatbath/Park Marquench Quenching and Tempering Salt

Category : Ceramic , Fluid , Quenchant

### Material Notes:

Low cost quench salt with slightly higher melting point and narrower working range than Low Temp Draw Salt and Thermo-Quench salts. It is as fluid as lower melting salts above 400°F offering equivalent quenching and drain off. (300 Parkettes) Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HeatbathPark-Marquench-Quenching-and-Tempering-Salt.php](http://www.lookpolymers.com/polymer_HeatbathPark-Marquench-Quenching-and-Tempering-Salt.php)

Thermal Properties	Metric	English	Comments
Melting Point	152 °C	305 °F	
Maximum Service Temperature, Air	593 °C	1100 °F	Upper limit of working range
Minimum Service Temperature, Air	177 °C	350 °F	Lower limit of working range

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China