

Heatbath/Park Nu-Sal High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

This barium-free salt is the most economical and most commonly used neutral salt for heat treating performed within its working range. It is non-hygroscopic and relatively non-corrosive to metal and fixtures. Formulated per MIL-S-10699-B, Class 5. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Nu-Sal-High-Speed-Hardening-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	666 Â°C	1230 Â°F	
Maximum Service Temperature, Air	899 Â°C	1650 Â°F	Upper limit of working range
Minimum Service Temperature, Air	704 Â°C	1300 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China