

Henkel Hysol EA 9394.2 Paste Adhesive System

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Fast cure adhesive for liquid shim and potting. Handling strength within 6 - 8 hours.Applications: Potting Structural Repair Liquid Shim

Order this product through the following link:

http://www.lookpolymers.com/polymer_Henkel-Hysol-EA-93942-Paste-Adhesive-System.php

Physical Properties	Metric	English	Comments
Storage Temperature	25.0 °C	77.0 °F	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	20.0 MPa	2900 psi	Tensile Lap Shear
	@Temperature -55.0 °C	@Temperature -67.0 °F	
	31.0 MPa	4500 psi	Tensile Lap Shear
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	107 °C	225 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 93.0 °C	@Temperature 199 °F	
	1440 min	24.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Pot Life	15 min	15 min	

Descriptive Properties	Value	Comments
Consistency	Thixotropic	
Form	2 parts	
Mix Ratio, Part A:Part B	100:27	
Peel Strength	Nil	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China