

## Henkel Hysol EA 9895 WPP Peel Ply

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

**Material Notes:**

Pre-impregnated, polyester peel ply product supplied in film form. Specially designed resin system capable of curing at 350°F / 177°C. Compatible with state-of-the-art composite prepreg resin systems. Provides minimal residual peel ply fibers at the bond surface after curing and removal. Applications: Composite Surfacing Composite Bonding

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Henkel-Hysol-EA-9895-WPP-Peel-Ply.php](http://www.lookpolymers.com/polymer_Henkel-Hysol-EA-9895-WPP-Peel-Ply.php)

Physical Properties	Metric	English	Comments
Storage Temperature	-18.0 °C	-0.400 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Glass Transition Temp, Tg	95.0 °C	203 °F	wet
	150 °C	302 °F	dry

Processing Properties	Metric	English	Comments
Cure Time	90.0 min	1.50 hour	
	@Temperature 177 °C	@Temperature 351 °F	

Descriptive Properties	Value	Comments
Out-Time (days)	14	at 25°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China