

Hexcel® Fibrelam® Grade 11 Panels for Aircraft Flooring

Category : Other Engineering Material

Material Notes:

Fibrelam® structural sandwich panels have been in service since 1973 and are currently approved for flooring by major aircraft manufacturers and airlines worldwide. These extensively flight-proven panels offer outstanding mechanical and physical properties, can be easily cut and machined on equipment normally found in airline maintenance shops, and are easy to install. Information provided by Hexcel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-Fibrelam-Grade-11-Panels-for-Aircraft-Flooring.php

Descriptive Properties	Value	Comments
Burn Length (mm)	71	BSS 7230; Flammability: 60 Second Vertical Ignition
Drip Extinguish Time (sec)	0	BSS 7230; Flammability: 60 Second Vertical Ignition
Glow Time (sec)	0	BSS 7230; Flammability: 45 Degree Test
Impact Resistance (N-m)	5.6	BMS 4-17
In-Plane Shear (N/mm)	110	BMS 4-17
Insert Shear (N)	4600	BMS 4-17
Long Beam Bending Deflection (mm)	11.7	MIL-STD-401B; At 445N (100lb)
Long Beam Bending Load (N)	1450	BSS 7250 Humidity; Humidity Resistance Load (100% at 60°C (140°F) for 30 days)
	2000	MIL-STD-401B; Core Ribbon, Transverse
Panel Shear Strength (N)	4900	MIL-STD-401B 3 point loading; Core Ribbon, Transverse
Sandwich Peel (N/76 mm)	400	MIL-STD-401B; Core Ribbon, Transverse
Self-Extinguish Time (sec)	3	BSS 7230; Flammability: 45 Degree Test
	6	BSS 7230; Flammability: 60 Second Vertical Ignition
Stabilized Core Compression (N/mm ²)	21.1	MIL-STD-401B
Warp (mm/m), max	0.8	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China