

Hexcel® HexForce™ 348 Aramid Fabric

Category : Other Engineering Material , Composite Fibers , Polymer , Thermoset , Aramid

Material Notes:

Hexcel manufactures aramid fabrics for use in aerospace applications as well as marine, tooling and recreational products where high strength, low weight, and impact resistance are essential. Aramids display excellent dimensional stability with a slightly negative coefficient of thermal expansion ($-2.4 \times 10^{-6}/^{\circ}\text{C}$.) They are resistant to chemicals with the exception of a few strong acids and alkalis. Aramids have excellent stability over a wide range of temperatures for prolonged periods. They show essentially no embrittlement or strength loss at temperatures as low as -320°F (-196°C). Aramids do not melt or support combustion but will start to carbonize at approximately 800°F (427°C). Information provided by Hexcel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexForce-348-Aramid-Fabric.php

Physical Properties	Metric	English	Comments
Thickness	221 microns	8.70 mil	
Fiber Count	422 dtex	380 denier	Warp yarn; Kevlar® 49
	422 dtex	380 denier	Fill yarn; Kevlar® 49

Mechanical Properties	Metric	English	Comments
Tensile Impact	347 J/cm	650 ft-lb/in	Filling
	352 J/cm	660 ft-lb/in	Warp

Thermal Properties	Metric	English	Comments
CTE, linear	$-2.40 \mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	$-1.33 \mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
Maximum Service Temperature, Air	427°C	801°F	starts to carbonize
Minimum Service Temperature, Air	-196°C	-321°F	

Descriptive Properties	Value	Comments
Fabric Weight (oz/yd ²)	4.9	Dry
Nominal Construction (count/in)	50	Warp
	50	Fill
Weave Style	8 Harness Satin	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China