

Hexcel[®] HexForce[™] 354 Aramid Fabric

Category : Other Engineering Material , Composite Fibers , Polymer , Thermoset , Aramid

Material Notes:

Hexcel manufactures aramid fabrics for use in aerospace applications as well as marine, tooling and recreational products where high strength, low weight, and impact resistance are essential. Aramids display excellent dimensional stability with a slightly negative coefficient of thermal expansion (-2.4 X 10-6/°C.) They are resistant to chemicals with the exception of a few strong acids and alkalis. Aramids have excellent stability over a wide range of temperatures for prolonged periods. They show essentially no embrittlement or strength loss at temperatures as low as -320°F (-196°C). Aramids do not melt or support combustion but will start to carbonize at approximately 800°F (427°C). Information provided by Hexcel

Order this product through the following link: http://www.lookpolymers.com/polymer_Hexcel-HexForce-354-Aramid-Fabric.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------|-------------|-----------------------|
| Thickness | 254 microns | 10.0 mil | |
| Fiber Count | 1580 dtex | 1420 denier | Warp yarn; Kevlar® 49 |
| | 1580 dtex | 1420 denier | Fill yarn; Kevlar® 49 |

| Mechanical Properties | Metric | English | Comments | |
|-----------------------|----------|--------------|----------|--|
| Tensile Impact | 303 J/cm | 568 ft-lb/in | Warp | |
| | 320 J/cm | 600 ft-lb/in | Filling | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|---------------|-----------------|---------------------|
| CTE, linear | -2.40 µm/m-°C | -1.33 µin/in-°F | |
| Maximum Service Temperature, Air | 427 °C | 801 °F | starts to carbonize |
| Minimum Service Temperature, Air | -196 °C | -321 °F | |

| Descriptive Properties | Value | Comments |
|---------------------------------|-------|----------|
| Fabric Weight (oz/yd2) | 4.9 | Dry |
| Nominal Construction (count/in) | 13 | Warp |
| | 13 | Fill |
| Weave Style | Plain | |

Contact Songhan Plastic Technology Co.,Ltd.



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China