

Hexcel® HexPly® 954-2A Curing Cyanate Resin, M60J Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-2A-Curing-Cyanate-Resin-M60J-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	1958 MPa @Temperature 23.0 °C	284000 psi @Temperature 73.4 °F	0°
Tensile Modulus	352 GPa @Temperature 23.0 °C	51100 ksi @Temperature 73.4 °F	0°
Flexural Yield Strength	1034 MPa @Temperature 23.0 °C	150000 psi @Temperature 73.4 °F	
Flexural Modulus	290 GPa @Temperature 23.0 °C	42100 ksi @Temperature 73.4 °F	
Compressive Yield Strength	869 MPa @Temperature 23.0 °C	126000 psi @Temperature 73.4 °F	
Compressive Modulus	324 GPa @Temperature 23.0 °C	47000 ksi @Temperature 73.4 °F	
Shear Strength	80.0 MPa @Temperature 22.0 °C	11600 psi @Temperature 71.6 °F	0°

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China