

Hexcel® HexPly® 954-6 Curing Cyanate Resin, K13C-2U Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-6-Curing-Cyanate-Resin-K13C-2U-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	19.0 MPa	2760 psi	90°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1799 MPa	260900 psi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Modulus	4.80 GPa	696 ksi	90°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	556 GPa	80600 ksi	0°
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Yield Strength	365 MPa	52900 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Modulus	558 GPa	80900 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Shear Strength	44.0 MPa	6380 psi	0°, IL
	@Temperature 22.0 °C	@Temperature 71.6 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China