

Hexcel® HexPly® EH04 Epoxy Resin System, MS40 Fiber

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

MS40 120 24" EF04 31%; Normalized to 55% fiber volume; 75°F, dry
Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-EH04-Epoxy-Resin-System-MS40-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2560 MPa	372000 psi	
Tensile Modulus	184 GPa	26700 ksi	
Flexural Yield Strength	1330 MPa	193000 psi	
Flexural Modulus	165 GPa	24000 ksi	
Compressive Yield Strength	1610 MPa	233000 psi	
Compressive Modulus	168 GPa	24300 ksi	
Shear Strength	84.1 MPa	12200 psi	Short Beam

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China