

## Hexcel® HexPly® EH04 Epoxy Resin System, T600 Fiber

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

**Material Notes:**

T24K 150 24" EH04 36%; Normalized to 55% fiber volume; 75°F, dry  
Information provided by HexCel

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexPly-EH04-Epoxy-Resin-System-T600-Fiber.php](http://www.lookpolymers.com/polymer_Hexcel-HexPly-EH04-Epoxy-Resin-System-T600-Fiber.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2270 MPa	329000 psi	
Tensile Modulus	118 GPa	17100 ksi	
Flexural Yield Strength	1480 MPa	214000 psi	
Flexural Modulus	114 GPa	16500 ksi	
Compressive Yield Strength	1650 MPa	240000 psi	
Compressive Modulus	123 GPa	17800 ksi	
Shear Strength	88.9 MPa	12900 psi	Short Beam

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China